


LuBoron™, LLC

ASTM D2596 FOUR BALL EXTREME PRESSURE MODEL 18

SPEED: 1770 (+/- 60) per 10 seconds HARDNESS: 64- 66 AISI-E52100 GRADE

GRADE: 25 extra polish TEMPERATURE: ambient



Load in Kilograms (more is better)

Boron: Last Non-Seizure Load:126 kg Weldpoint:500 kg Load Wear Index:101.9

Valvoline: LNSL - 63 K WELDPOINT - 250 kg LWI-35.3

Source: Falex Corporation, Aurora IL